

GALE
COMMERCIAL

Commercial
Heavy

Product Profile



The Engineered Standard for
Broad-Span Architectural Shade

Commercial Heavy is a premium, heavyweight HDPE shade fabric engineered for vast structures and high-wind environments, utilising a patented intertwining knit to deliver unparalleled tear resistance and dimensional stability. Designed for large-scale architectural projects where scale and precision are paramount, its advanced construction provides a visually striking appearance with superior abrasion resistance and water-shedding properties that perform year after year.

Features and Benefits

- **Dimensional Stability:** Stentered (heat-set) to prevent deformation and simplify fabrication, minimising re-tensioning, and maintenance costs.
- **Extreme Strength:** 100% virgin grade polymers in a monofilament construction for superior tensile strength, rot-proof performance, and moisture resistance.
- **Fade-Resistant Palette:** Available in 16 architectural colours, with UV-stabiliser components engineered in the raw material to ensure long-lasting colour performance.



For more information, visit galecommercial.com

GLOBAL CUSTOMER SUPPORT
commercialsupport@galecommercial.com

SALES - ANZ
Toll Free: +1 800 331 521
anz@galecommercial.com

SALES - ASIA / EUROPE
Toll Free: +1 800 331 521
eurasia@galecommercial.com

SALES - AMERICAS
Toll Free: +1 800 560 4667
americas@galecommercial.com

SALES - MIDDLE EAST / AFRICA
+971 4 881 7114
mena@galecommercial.com

Technical Specifications

Fabric Properties		
	Metric - AS 2001.2.13 (mass per unit)	Imperial - ASTM D3776 (mass per unit)
Nominal Fabric Mass	430 gsm ± 20	12.7 oz / yd ²
Approx. Thickness	1.6 mm	0.06 in
Roll Specifications		
	Metric (mass per unit)	Imperial (mass per unit)
Nominal Width	3.0 m	9 ft 10 in
Length	40 m	131 ft 3 in
Approx. Roll Weight	54 kg	119 lbs
Approx. Roll Diameter	0.30 m	1 ft
Core Diameter	76 mm	3 in

Performance Data

Flammability		
Certification	Test	Value
AS 1530.2-Part 2 - Flammability Test	Flammability Index (Range 0-100)	21
	Ignitability Index (Range 0-20)	9
AS 1530.3-Part 3 - Early Fire Hazard Test	Spread of Flame Index (Range 0-10)	9
	Heat Evolved Index (Range 0-10)	4
	Smoke Developed Index (Range 0-10)	5

Maximum Force And Elongation - Strip Method (AS 2001.2.3.1-2001)	
Maximum Force - Warp (Mean)	1600 N/50mm
Elongation at Maximum Force - Warp (Mean)	108 %
Maximum Force - Weft (Mean)	1400 N/50mm
Elongation at Maximum Force - Weft (Mean)	165 %

Breaking Force - Grab Test (AS 2001.2.3.2-2001)	
Breaking Force - Warp (Mean)	1800 N
Breaking Force - Weft (Mean)	1600 N

Tear Resistance - Wing Rip Method (AS 2001.2.10-1986)	
Wing Tear - Warp (Mean)	503 N
Wing Tear - Weft (Mean)	255 N

Bursting Pressure - Hydraulic Diaphragm Method (AS 2001.2.4)	
Bursting Pressure (Mean)	3900 kPa

Bursting Force - Ball Burst Method (AS 2001.2.19-1988)	
Bursting Force (Mean)	2349 N

Shade Protection Fabric Performance (AS 4174:2018)							
Colour	Cover Factor	Shade Factor	UV-vis Trans %	UVR Trans %	UVR Block %	UVE %	Protection Category
Aquatic Blue	87	85.5	14.5	12.7	87.3	87	Effective
Black	86	86.4	13.6	13.6	86.4	86	Effective
Bright Green	86	85.2	14.8	13.2	86.8	86	Effective
Brunswick Green	86	86.7	13.3	13.2	86.8	86	Effective
Charcoal	87	87.5	12.5	12.4	87.6	87	Effective
Cherry Red	87	76.0	24.0	12.6	87.4	87	Effective
Deep Ochre	87	87.0	13.0	12.7	87.3	86	Effective
Desert Sand	85	79.0	21.0	14.1	85.9	85	Effective
Emerald	86	84.7	15.3	13.3	86.7	86	Effective
Natural	88	73.9	26.1	12.1	87.9	87	Effective
Navy Blue	87	86.8	13.2	12.5	87.5	87	Effective
Orange	86	75.9	24.1	13.2	86.8	86	Effective
Royal Purple	86	85.0	15.0	13.5	86.5	86	Effective
Steel Grey	86	85.5	14.5	13.5	86.5	86	Effective
White	86	69.0	31.0	13.4	86.6	86	Effective
Yellow	86	70.3	29.7	13.9	86.1	85	Effective

*Test results available upon request. Each colour individually tested and passes all certification criteria for above. Available in Flame Retardant and Non-Flame Retardant. Biaxial elastic material properties available on request. Select colors only available in made to order.

Care & Maintenance

Do not use near open flames. Avoid contact with organic solvents, halogens, or highly acidic substances, as these will reduce service life and void the warranty.